


Simulation of NAPTF High Tire Pressure Tests with Advanced Finite Element Modeling

Hao Wang, Ph.D. Rutgers University
Maoyun Li, Rutgers University
Navneet Garg, Ph.D. FAA

Aircraft Tire Pressure Trend



(After C. Fabre, 2009)

Objective and Scope

- Develop a 3-D viscoelastic finite element model for airfield pavement test sections at NAPTF
- Evaluate effect of aircraft tire pressure on pavement responses and rutting using different temperature profiles
 - 1.45MPa (210psi) vs. 1.69MPa (245psi)

Calculation of Pavement Response

Layered Elastic Theory


- □ Simple loading and material assumption
- □ Public software available
- □ Fast computation speed

Finite Element Method

- □ Complex loading condition and material properties
- □ Flexible geometry and discontinuities (joint, crack, interface, interlayer, et al.)
- □ Large computation resource and time

3-D FE Pavement Modeling


- Moving tire load with pre-defined contact area and stress
- Quasi-static or dynamic analysis
- Viscoelastic asphalt layer
- Nonlinear anisotropic unbound layer
- □ Frictional interface




Element Size and Boundary Conditions


- □ Element vertical size:
 - 12.7 mm for HMA layer
 - 40-50 mm for base layer
- □ Element horizontal dimension:
 - ☐ 10-20 mm in the transverse direction.
 - 40 mm in the longitudinal (moving) direction
- □ Infinite elements used to reduce degrees of freedom and create "silent" boundaries
- Coulomb frictional interfaces are used


Determination of FE Model Size



Pavement Structure









Material Characterization








t is relaxation time.


HMA Linear Viscoelasticity

 Generalized Maxwell Solid Model: Consists of one spring and n Maxwell elements connected in parallel




 Relaxation modulus is converted from dynamic modulus and expressed as Prony Series


Non-Uniform Tire Contact Stress





Wang, H., I.L. Al-Qadi, and I. Stanciulescu, Simulation of Tire-Pavement Interaction for Predicting Contact Stresses at Static and Rolling Conditions,. International Journal of Pavement Engineering, Vol. 13, No.4, 2012, pp. 310-321

Changes in Tire Contact Pressure under Aircraft Load










Non-uniform Pressure Distribution

(1.69MPa and 1.45MPa)


Contact pressure assumptions		Contact width (mm)	Contact length (mm)	Peak pressure (MPa)	
Non- uniform	Rib 1	60	440 / 520	4.23 / 3.63	
	Rib 2	50	440 / 520	2.11 / 1.74	
	Rib 3	120	440 / 520	2.11 / 1.74	
	Rib 4	50	440 / 520	2.11 / 1.74	
	Rib 5	60	440 / 520	4.23 / 3.63	
	Groove	15	440 / 520	0	


Importance of Moving Load



- Loading time varies at various pavement depths and directions
- Principal stresses rotate under a moving load


Simulation of Tire Loading






In-depth Strain Distribution

(measured temperature profile at NAPTF)





Effect of Tire Pressure on Responses

Tire load: 272.7kN (61.3kips)	Measured Temperature Profile			Reversed Temperature Profile		
Tire pressure (MPa)	1.45	1.69	Change	1.45	1.69	Change
Critical tensile strain (µ)	1068	1339	+25%	899	1101	+22%
Shear strain (μ)	6049	6617	+9%	8158	8891	+10%
Compressive strain (µ)	8496	9225	+9%	14119	15614	+11%
Deviator Stress (kPa)	2107	2489	+18%	1823	2154	+18%

Calculation of Rutting Depth (MEPDG)

$$\begin{split} \frac{\mathcal{E}_p}{\mathcal{E}_r} &= k_1 * 10^{-3.4488} T^{1.5606} N^{0.479244} \\ k_1 &= (C_1 + C_2 * depth) * 0.328196^{depth} \\ C_1 &= -0.1039 * h_{ac}^2 + 2.4868 * h_{ac} - 17.342 \\ C_2 &= 0.0172 * h_{ac}^2 - 1.7331 * h_{ac} + 27.428 \end{split}$$

where,

k₁ = function of total asphalt layers thickness (h_{ac}, in) and depth (depth, in) to computational point, to correct for the confining pressure at different depths

$$RD_{AC} = \sum_{i=1}^{N} (\varepsilon_p)_i \cdot \Delta h_i$$
 $RD_{AC} = \text{rut depth at the asphalt concrete layer}$ $N = \text{number of sublayers}$ $(\varepsilon_p)_i = \text{vertical plastic strain at mid-thickness of layer i}$ $\Delta h_i = \text{thickness of sublayer i}$

Calculation of Rutting Depth (AI)

$$Log\left(\frac{\varepsilon_{p}}{\varepsilon_{r}}\right) = -6.631 + 0.4354Log(N) + 2.767Log(T) + 0.110Log(\sigma_{d}) - 0.118Log(\eta) + 0.930Log(V_{beff}) + 0.501Log(V_{a})$$

where

 σ_d = deviator stress, psi.

 η = viscosity of the asphalt binder at 70°F, × 10° poise.

 V_{beff} = effective asphalt content by volume, percent.

 V_a = air void volume, percent.


$$RD_{AC} = \sum_{i=1}^{N} \left(\varepsilon_{p}\right)_{i} \cdot \Delta h_{i}$$
 $RD_{AC} = \text{rut depth at the asphalt concrete layer}$ $N = \text{number of sublayers}$ $(\varepsilon_{p})_{i} = \text{vertical plastic strain at mid-thickness of layer i}$ $\Delta h_{i} = \text{thickness of sublayer i}$


Effect of Tire Pressure on Rutting Depth

Tire load: 272.7kN (61.3kips)	Al Model			MEPDG model		
Tire pressure: Mpa (psi)	1.45 (210)	1.69 (245)	Change	1.45 (210)	1.69 (245)	Change
Rut depth (in.)	Measured temperature profile at NAPTF					
400th cycle	1.40	1.56	+11%	0.65	0.71	+9%
800th cycle	1.90	2.11	+11%	0.91	1.00	+10%
Rut depth (in.)	Reversed ten			nperature profile		
400th cycle	1.55	1.74	+12%	0.77	0.85	+10%
800th cycle	2.09	2.35	+12%	1.08	1.19	+10%

Simulation of Wander Pattern


Wander during APT






(After Monismith et al. 2006)

Effect of Wandering on Rutting



Conclusions

- The high tire pressure causes greater responses by different percentages
 - Temperature profile affects maximum pavement responses
 - Changes of maximum strain responses due to tire pressure are not affected by temperature variation
- The high tire pressure causes slightly greater rutting depth
 - Calibration is needed to predict accurate rutting depth



Thank You Questions?

Hao Wang hwang.cee@rutgers.edu